

# VENTURE TAPE

## HVAC Cloth Duct Tape 1500



Typical Usage – Sealing Metal Ductwork  
 Shear Strength: 2.2 psi Indefinite  
 Peel Adhesion: 34 oz/in  
 Tensile Strength: 34 lb/inch width  
 Low Application Temperature: 40 F  
 High Temperature Resistance: 175 F

Mfg Part No	Width (in)	Length (yds)	Thickness (mil)	Color
1500	3	60	10	Silver
1500	3	60	10	White
1500	3	60	10	Black
1500	2	60	10	Silver
1500	2	60	10	White
1500	2	60	10	Black

## Foil HVAC Tape 1520CW



Typical Usage – Sealing Sheet Metal and Fiberglass Ducts  
 Shear Strength: 2.2 psi indefinite  
 Peel Adhesion: 96 oz/in  
 Tensile Strength: 27 lb/inch width  
 Low Application Temperature: -35 F  
 High Temperature Resistance: 260 F

Mfg Part No	Width (in)	Length (yds)	Thickness (mil)	Color
1520CW	2	50	3.5	Silver
1520CW	2.5	50	3.5	Silver
1520CW	3	50	3.5	Silver

## Foil HVAC Tape 1525CW FSK



Typical Usage – Sealing Fiberglass Blanket and Ductboard FSK Faced Systems  
 Shear Strength: 2.0 psi indefinite  
 Peel Adhesion: 92 oz/in  
 Tensile Strength: 40 lb/inch width  
 Low Application Temperature: -25 F  
 High Temperature Resistance: 175 F

Mfg Part No	Width (in)	Length (yds)	Thickness (mil)	Color
1525CW FSK	3	50	6.5	Silver

**VentureTape®**

## Foil HVAC Tape 1581A



Typical Usage – Sealing Flexible Ductboard  
 Shear Strength: 2.2 psi indefinite  
 Peel Adhesion: 66 oz/in  
 Tensile Strength: 25 lb/inch width  
 Low Application Temperature: -20 F  
 High Temperature Resistance: 260 F

Mfg Part No	Width (in)	Length (yds)	Thickness (mil)	Color
1581A	2.5	60	4.0	Silver
1581A	3	60	4.0	Silver

## UL 181B-FX Printed Tape

### 1599B



Typical Usage – Sealing Flexible Ducts  
 Shear Strength: 2.2 psi indefinite  
 Peel Adhesion: 41 oz/in  
 Tensile Strength: 22 lb/inch width  
 Low Application Temperature: -35 F  
 High Temperature Resistance: 260 F

Mfg Part No	Width (in)	Length (yds)	Thickness (mil)	Color
1599B	2	120	3.0	Clear
1599B	3	120	3.0	Clear
1599B	2	120	3.0	Black
1599B	3	120	3.0	Black
1599B	2	120	3.0	Silver
1599B	3	120	3.0	Silver

## Foil HVAC Tape 3520CW



Typical Usage – High Strength Sealing of Fiberglass Ductboard and Sheet Metal Ducts  
 Shear Strength: 2.2 psi indefinite  
 Peel Adhesion: 100 oz/in  
 Tensile Strength: 34 lb/inch width  
 Low Application Temperature: -35 F  
 High Temperature Resistance: 260 F

Mfg Part No	Width (in)	Length (yds)	Thickness (mil)	Color
3520CW	2	50	3.7	Silver
3520CW	2.5	50	3.7	Silver
3520CW	3	50	3.7	Silver

VENTURE TAPE

Albany, NY	518-489-0010	Rochester, NY	585-482-3876	Allentown, PA	610-437-9818	Scranton, PA	570-346-1565
Binghamton, NY	607-724-2451	Syracuse, NY	315-475-3131	Altoona, PA	814-941-7617	Stroudsburg, PA	570-424-5724
Buffalo, NY	716-853-1291	Utica, NY	315-732-4077	Erie, PA	814-459-4559	Wilkes-Barre, PA	570-824-8779
Middletown, NY	845-733-5666			Harrisburg, PA	717-558-0828	Williamsport, PA	570-323-4606